



Preliminary Tuft Testing of Metallic Bristles Versus PS212, PS300, and HVOF300

James A. Fellenstein
Ohio Aerospace Institute
Cleveland, Ohio

Christopher DellaCorte
Lewis Research Center
Cleveland, Ohio

The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at **<http://www.sti.nasa.gov>**
- E-mail your question via the Internet to **help@sti.nasa.gov**
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:
NASA Access Help Desk
NASA Center for AeroSpace Information
800 Elkridge Landing Road
Linthicum Heights, MD 21090-2934



Preliminary Tuft Testing of Metallic Bristles Versus PS212, PS300, and HVOF300

James A. Fellenstein
Ohio Aerospace Institute
Cleveland, Ohio

Christopher DellaCorte
Lewis Research Center
Cleveland, Ohio

Prepared for the
Annual Meeting
sponsored by the Society of Tribologists and Lubrication Engineers
Detroit, Michigan, May 17-21, 1998

National Aeronautics and
Space Administration

Lewis Research Center

Available from

NASA Center for Aerospace Information
800 Elkridge Landing Road
Lythicum, MD 21090-2934
Price Code: A02

National Technical Information Service
5287 Port Royal Road
Springfield, VA 22100
Price Code: A02

Preliminary Tuft Testing of Metallic Bristles Versus PS212, PS300, and HVOF300

James A. Fellenstein*
Ohio Aerospace Institute
Cleveland, Ohio

Christopher DellaCorte
NASA Lewis Research Center
Cleveland, Ohio

Abstract

Turbine engine brush seals are designed with sacrificial brushes and hard shaft coatings to minimize shaft wear and reduce the cost of engine overhauls. Replacing a worn seal is more cost and time effective than refinishing an engine shaft. However, this tribological design causes excessive brush wear and reduces long term seal efficiency.

An alternative approach is to coat the shaft with a solid lubricant and allow the bristles to wear into the shaft coating similar to traditional abradable labyrinth seals. This approach can result in reduced seal leakage by forcing the leakage to flow through the seal bristle pack or through a more tortuous shaft wear track. Key to this approach is limiting the shaft wear to an acceptable level where surface refinishing would not be required during every engine overhaul.

Included in this paper are brush seal tuft test results for four metallic bristles (nickel-chrome or cobalt-chrome based superalloys) tested against three solid lubricant coatings (NASA's PS212, PS300, and HVOF300). These test results are also compared to previous baseline tests conducted with plasma sprayed chrome carbide. Compared to the baseline results, no tribological benefit was achieved with the metallic bristle/solid lubricant tribopairs tested. To improve the performance of the solid lubricant coatings, issues regarding lubricant phase sizes (homogeneity), and composition need to be addressed.

Introduction

A typical brush seal is made with fine wires densely packed between two plates (Figure 1). To allow the bristles to deflect and follow shaft excursions the bristles are set at a forty-five degree angle from the shaft. This ability to respond to shaft eccentricities without losing sealing performance gives the brush seal an advantage over traditional labyrinth seals. Brush

seals, even when worn line-to-line with the shaft, have lower leakage rates than typical labyrinth seals. However, the minimum seal leakage of a brush seal occurs before the designed interference fit between the seal and shaft wears away. Low bristle-to-rotor friction is also important to minimize heat generation in rotor components already operating close to their temperature-stress limit. Therefore, to maximize overall turbomachinery efficiency, brush seal interfacial wear and friction should be minimized (ref. 1).

Traditionally, brush seals are designed with a hard shaft coating and a sacrificial brush. This is done to reduce surface wear and the costly expense of surface refinishing during engine overhauls. The trade-off of using hard shaft coatings is excessive brush wear and reduced long term seal performance. Solid lubricants provide an opportunity to improve the long term seal performance by wearing in much like an abradable labyrinth seal. In other words, the seal would wear line-to-line below the shaft's unworn outer diameter forcing leakage flow to pass through the wear track or directly through the brush bristle pack creating a labyrinth type flow restriction. Minimizing shaft wear to an acceptable level without refinishing at every overhaul interval is crucial to the success of using solid lubricants.

To investigate the possibility of using solid lubricants for brush seal applications, two NASA developed coatings were tested against four metallic bristle materials. Characterization of each tribopair included measuring the friction coefficient along with the brush and journal wear factors.

The results of these tests are also compared to previously tested metallic bristles versus (75–25 wt%) plasma sprayed chrome carbide (ref. 2). Included in this comparison is data for H25, a cobalt chrome superalloy, against plasma sprayed chrome carbide which represents the industry standard and the baseline for this study.

*NASA Resident Research Associate at Lewis Research Center

Specimen Materials and Preparation

The three coatings tested were PS212, PS300, and HVOF300. PS212 is a plasma sprayed chrome carbide based solid lubricant. Two versions of the chrome oxide based 300 series coating were tested (plasma sprayed and high velocity oxygen flame sprayed). Both the 200 and 300 series coatings have added silver for low temperature lubrication and barium fluoride/calcium fluoride eutectic for high temperature lubrication (refs. 3, 4, and 5). Coating compositions are presented in Table 1.

Before testing each journal is diamond ground to 38.1 mm (1.5 in.) diameter with a surface roughness less than $0.4\text{ }\mu\text{m}$ ($16\text{ }\mu\text{in.}$). Typical coating thickness is 0.25 mm (0.010 in.). Figure 2 shows the final journal configuration.

The four wire materials tested were H25, I718, H230, and H242 (see Table 2 for compositions). These materials were all selected because of their high temperature capabilities and their availability in wire form.

Each tuft is made with 920 bristles welded into a superalloy collar. The wire diameter for each material was 0.071 mm (0.0028 in.). After welding, the tufts are diamond ground to a 45° angle simulating an actual brush seal interface (Figure 3).

For additional information regarding test specimens or facility used see reference 6.

Test Apparatus and Procedures

These tests were completed on the Brush Seal Tuft Test Rig at the NASA Lewis Research Center (Figure 4). One advantage of this facility is it allows tufts to be tested with a constant contact pressure. This constant load allows accurate tribological measurements of both the tuft and journal without the confounding effects of unsteady loads and pressure differentials. The maximum test spindle speed and test temperature are 17,000 RPM and 800°C (1292°F) respectively. When mounting the test journals, the total indicated runout was limited to less than 0.009 mm (0.00035 in.). This facility has been shown to characterize candidate brush seal materials accurately at about $1/10^{\text{th}}$ the cost of full scale seal testing (ref. 2).

Two tufts were made for each of the material combinations tested. Each tuft was tested in two, twenty-five hour segments. The standardized test temperature, surface speed, and contact pressure were 650°C (1200°F), 24 m/s (78.5 ft/s), and 75.8 kPa (11 psi) respectively. During each test the friction force, temperature, and speed were measured with a ± 250 gram linear




Figure 1.—Schematic of a typical brush seal showing front and cross section views.




Figure 2.—Journal specimen configuration showing dimensions and geometry (dimensions in cm).




Figure 3.—Tuft specimen configuration showing dimensions and geometry (dimensions in cm).




Figure 4.—Cross section side view of brush seal tuft test rig.




Figure 5.—Average friction coefficients for four metallic bristles tested against three solid lubricants and plasma sprayed chrome carbide at 650 °C (1200 °F).




Figure 6.—Brush wear factors for four metallic bristles tested against three solid lubricants and plasma sprayed chrome carbide at 650 °C (1200 °F).

voltage displacement transformer (LVDT load cell), a Type K thermocouple and an optical speed pick-up respectively. The brush wear was calculated from the difference in bristle lengths from inscribed witness marks. To facilitate these measurements, low magnification photomicrographs (25x) were taken before and after each test segment. Post test analysis of the journals is completed by measuring the circumferential wear track cross sectional area with a stylus type surface profilometer at 90° intervals around the journal. Finally, wear factors for both the brush and journal are calculated based on the measured wear, test load, and sliding distance.

Results and Discussion

As seen in Figure 5 the friction coefficients ranged from 0.25 to 0.45 except for the tests conducted with the H242. In both tests completed with H242 the friction coefficient was above 0.60. Brush wear factors ranged from $2.9 \times 10^{-7} \text{ mm}^3/\text{N}\cdot\text{m}$ (low wear) for I718 against PS300 to $4.8 \times 10^{-6} \text{ mm}^3/\text{N}\cdot\text{m}$ (moderate wear) for H230 against PS300 (Table 3 and Figure 6). Journal wear factors ranged from $2.7 \times 10^{-8} \text{ mm}^3/\text{N}\cdot\text{m}$ (low wear) for I718 against plasma sprayed chrome carbide to $6.6 \times 10^{-6} \text{ mm}^3/\text{N}\cdot\text{m}$ (moderate wear) for H25 against PS212 (Table 3 and Figure 7).




Figure 7.—Journal wear factors for four metallic bristles tested against three solid lubricants and plasma sprayed chrome carbide at 650 °C (1200 °F).

Average friction coefficients for H25, I718, and H230 against plasma sprayed chrome carbide are 0.32, 0.28, and 0.24 respectively (ref. 2). Comparing these results to those of the two plasma sprayed solid lubricants (PS212 and PS300), the friction coefficients were within 10% for each of the three wire materials. The HVOF300 had friction values over 30% higher.

In previous tests with the tribopair IX750, a nickel chrome superalloy, sliding against PS212 reported by Hawthorne (ref. 7), a higher overall wear rate was exhibited than IX750 sliding against chrome carbide. As pointed out by Hawthorne, PS212 has a heterogeneous surface with lubricant phase sizes larger than the diameter of the brush materials. The result of these oversized lubricant phases is preferential removal of the lubricants from the surface, what remains is a very rough, low density nickel-chrome bonded chrome carbide that causes excessive brush and journal wear. This same phenomena was observed in the H25 versus PS212 test. Out of the four tests completed with H25, the test against PS212 had the highest journal and brush wear. After this was observed no additional tests were conducted with the PS212.

As previously reported, the H230 bristles began to flair after 50 hours of testing against the plasma sprayed chrome carbide (ref. 2). This same phenomena was observed with the H230 against the PS300. Due to the severity of the flaring the brush wear factor was estimated to be $2.8 \times 10^{-7} \text{ mm}^3/\text{N}\cdot\text{m}$. Based on the bristle flaring observed in these tests no additional H230 tests were completed.

Compared to HVOF300, the PS300 consistently had a lower friction coefficient and a lower brush wear factor for two of the

three wire/counterface combinations. This result was expected due to the lower density of the plasma sprayed version. Furthermore, the improved coating density of the HVOF300 resulted in lower journal wear factors against the H242 and H25 (Figure 7).

Among the metallic brush/lubricant coating combinations tested, I718/PS300 was the best. However, compared to the baseline H25/PS Cr_2C_3 , the I718/PS300 wear couple exhibited more than seven times greater journal wear without a significant improvement in friction and only a modest reduction in brush wear. Based on these results the metallic brush/solid lubricant tribopairs tested did not provide any additional tribological benefits over the industry standard of H25 against plasma sprayed chrome carbide.

Concluding Remarks

The results, especially for I718/PS300, show that tuft wear can be reduced by incorporating solid lubricants in the shaft coating. However, shaft wear increased dramatically. This observation corroborates that of Hawthorne suggesting that improving coating uniformity and reducing lubricant phase size may improve performance. Future work may include coating optimization and testing of other tuft materials including advanced ceramics.

References

1. Mahler, F., and Boyes, E., "The Application of Brush Seals in Large Commercial Jet Engines," AIAA paper 95-2617, 1995.
2. Fellenstein, J.A., DellaCorte, C., Moore, K., and Boyes, E., "High Temperature Brush Seal Tuft Testing of Metallic Bristles Versus Chrome Carbide," NASA TM-107238, AIAA paper 96-2908, 1996.
3. DellaCorte, C., and Sliney, H., "Composition Optimization of Self Lubricating Chromium-Carbide-Based Composition for Use to 760°C," ASLE volume 30, 1, 77-83, 1986.
4. DellaCorte, C., and Edmonds, B.J., "Preliminary Evaluation of PS300: A New Self-Lubricating High Temperature Composition Coating for Use to 800°C," NASA TM-107056, 1996.
5. DellaCorte, C., and Laskowski, J.A., "Tribological Evaluation of PS300: A New Chrome Oxide Based Solid Lubricant Coating Sliding Against Al_2O_3 From 25 to 650°C," NASA TM-107163, 1996.
6. Fellenstein, J.A., and DellaCorte, C., "A New Tribological Test for Candidate Brush Seal Materials Evaluation," NASA TM-106753, 1995.
7. Hawthorne, H.M., "Brush-on-disc simulation tribotesting of materials for gas turbine-compliant seal components," Tribology International, Volume 27 Number 2, 1994.

Table 1: Coating Compositions by Weight and Percent Volume of PS212, PS300, HVOF300

Coating	Constituent, wt.% (vol. %)			
Designation	Ni-Co-Cr ₂ C ₃ *	NiCr-Cr ₂ O ₃ **	Ag	BaF ₂ /CaF ₂
PS212	70 (67)	—	15 (9)	15 (24)
PS300 and HVOF300	—	80 (80)	10 (6)	10 (14)

* By wt.% contains 54 Cr₂C₃, 28 Ni, 12 Co, 2 Mo, 2 Al, 1 B, and 1 Si

**By wt.% contains 80 Cr₂O₃, 16 Ni, and 4 Cr
refs. 4, 5, and 6

Table 2: Chemical Composition of Wire Samples (wt.%)

	Co	Ni	Cr	Fe	W	Mo	OTHERS (< 6 wt.%)
H25	51	10	20	3	15	—	Mn, Si, C
I718	—	52.5	19	18.5	—	3	Nb, Ti, Al, C, Cu
H230	5	52.7	22	3	14	2	Si, Mn, C, Al, B, La
H242	2.5	60	8	2	—	25	Mn, Cu, Al, Si, C, B

Table 3: Wear Factor Interpretation

Wear Factor (mm ³ /N•m)	Interpretation
>10 ⁻⁴	High Wear
10 ⁻⁵ to 10 ⁻⁶	Moderate to Low Wear
<10 ⁻⁷	Low Wear

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 1998		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE Preliminary Tuft Testing of Metallic Bristles Versus PS212, PS300, and HVOF300			5. FUNDING NUMBERS WU-523-22-13	
6. AUTHOR(S) James A. Fellenstein and Christopher DellaCorte				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-10835	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-107522	
11. SUPPLEMENTARY NOTES Prepared for the Annual Meeting sponsored by the Society of Tribologists and Lubrication Engineers, Detroit, Michigan, May 17-21, 1998. James A. Fellenstein, Ohio Aerospace Institute, 22800 Cedar Point Road, Cleveland, Ohio 44142 and NASA Resident Research Associate at Lewis Research Center (work funded by NASA Cooperative Agreement NCC3-440); Christopher DellaCorte, NASA Lewis Research Center. Responsible person, James A. Fellenstein, organization code 5140, (216) 433-6065.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Category: 23 This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Turbine engine brush seals are designed with sacrificial brushes and hard shaft coatings to minimize shaft wear and reduce the cost of engine overhauls. Replacing a worn seal is more cost and time effective than refinishing an engine shaft. However, this tribological design causes excessive brush wear and reduces long term seal efficiency. An alternative approach is to coat the shaft with a solid lubricant and allow the bristles to wear into the shaft coating similar to traditional abradable labyrinth seals. This approach can result in reduced seal leakage by forcing the leakage to flow through the seal bristle pack or through a more tortuous shaft wear track. Key to this approach is limiting the shaft wear to an acceptable level where surface refinishing would not be required during every engine overhaul. Included in this paper are brush seal tuft test results for four metallic bristles (nickel-chrome or cobalt-chrome based superalloys) tested against three solid lubricant coatings (NASA's PS212, PS300, and HVOF300). These test results are also compared to previous baseline tests conducted with plasma sprayed chrome carbide. Compared to the baseline results, no tribological benefit was achieved with the metallic bristle/solid lubricant tribopairs tested. To improve the performance of the solid lubricant coatings, issues regarding lubricant phase sizes (homogeneity), and composition need to be addressed.				
14. SUBJECT TERMS Seal; Brush seal; Solid lubricants			15. NUMBER OF PAGES 10	
			16. PRICE CODE A02	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	